

Density of States and NMR Relaxation Rate in Anisotropic Superconductivity with Intersecting Line Nodes

Yasumasa HASEGAWA

February 9, 2008

Faculty of Science, Himeji Institute of Technology,
Kamigori, Akou-gun, Hyogo 678-12.

July 12, 1996

Abstract

We show that the density of states in an anisotropic superconductor with intersecting line nodes in the gap function is proportional to $E \log(\alpha \Delta_0/E)$ for $|E| \ll \Delta_0$, where Δ_0 is the maximum value of the gap function and α is constant, while it is proportional to E if the line nodes do not intersect. As a result, a logarithmic correction appears in the temperature dependence of the NMR relaxation rate and the specific heat, which can be observed experimentally. By comparing with those for the heavy fermion superconductors, we can obtain information about the symmetry of the gap function.

Recently, many effects related to the anisotropic superconductivity have been observed experimentally in heavy fermion superconductors. [1, 2, 3, 4, 5, 6, 7] The density of states near the Fermi surface is determined experimentally by observing the temperature dependence of the specific heat (C) and the relaxation rate (T_1^{-1}) of NMR and NQR. It is well known that if the density of states, $N(E)$, is proportional to E^n , $1/T_1 \propto T^{2n+1}$ and $C \propto T^{n+1}$. [8, 9]

Although the symmetry of the gap function in heavy-fermion superconductors has not been determined, $T_1^{-1} \propto T^3$ has been observed in NMR and NQR experiments for $T < T_c$ in heavy fermion superconductors (UBe₁₃, CeCu₂Si₂, UPt₃, URu₂Si₂, and UPd₂Al₃). [1, 2, 3, 4, 5, 6, 7] This suggests the existence of line nodes in the gap function $\Delta(\mathbf{k})$. [9] As the simplest model for anisotropic superconductivity with line nodes in the gap function at the Fermi surface, the p -wave polar state has been extensively studied. The gap function for the polar state is given by

$$\Delta_{\mathbf{k},\text{polar}} = \Delta_0 \cos \theta, \quad (1)$$

where $\cos \theta = k_z/|\mathbf{k}|$. The effects of impurities has also been studied theoretically for the p -wave polar and axial states. [10, 11, 12] However, the p -wave state is not consistent with the decrease in the Knight shift below T_c observed in UPd₂Al₃, [6, 7] which indicates that the pairing has even parity in that system. For even parity pairing we have to consider the d -wave or higher wave pairing state. If we consider higher wave paring states with line nodes in the gap function on the Fermi surface, the line nodes intersect in some cases. For example, the line nodes intersect at $(0, 0, \pm k_F)$ on the Fermi surface for the state with the d -wave gap function, $\Delta_{\mathbf{k}} \propto k_x^2 - k_y^2$ or $\Delta_{\mathbf{k}} \propto k_x k_y$. Although intersection of the line nodes on the Fermi surface may not be favored by the condensation energy, it is not forbidden by the symmetry.

T^3 dependence of T_1^{-1} has also been observed in high T_c superconductors [13, 14] and organic superconductors. [15, 16] Anisotropic superconductivity with line nodes is also thought to be realized in these materials. Since these superconductors have low-dimensional Fermi surfaces, the line nodes in the gap function are not likely to intersect on the Fermi surface.

It is often stated that $N(E) \propto E^2$ in the case of point nodes and $N(E) \propto E$ in the case of line nodes. [8, 9] However, it has not been noticed, as far as the author knows, that $N(E) \propto E$ only when line nodes do not intersect. In this work we show that when the gap function is zero on the intersecting lines, $N(E) \propto E \log(\alpha \Delta_0/E)$, where α is constant and Δ_0 is the maximum value of the gap function. As a result, the temperature dependence of T_1^{-1} differs significantly from that for the case with non-intersecting line nodes.

We assume a spherical Fermi surface. The density of states is given by

$$N(E) = N_0 \int \frac{d\Omega}{4\pi} \text{Im} \frac{E}{\sqrt{\Delta_{\mathbf{k}}^2 - E^2}}, \quad (2)$$

where the density of states for the normal state, N_0 , is constant and the gap function $\Delta_{\mathbf{k}}$ depends only on the direction of $\mathbf{k}$.

The density of states for the polar state is given by

$$\frac{N_{\text{polar}}(E)}{N_0} = \begin{cases} \frac{\pi}{2} \frac{E}{\Delta_0} & \text{if } E < \Delta_0 \\ \frac{E}{\Delta_0} \arcsin \frac{\Delta_0}{E} & \text{if } E \geq \Delta_0 \end{cases}. \quad (3)$$

We calculate the density of states for the state with the gap function given by

$$\begin{aligned} \Delta_{\mathbf{k}, x^2-y^2} &= \Delta_0 \frac{k_x^2 - k_y^2}{|\mathbf{k}|^2} \\ &= \Delta_0 \sin^2 \theta \cos 2\phi, \end{aligned} \quad (4)$$

or

$$\begin{aligned}\Delta_{\mathbf{k},xy} &= \Delta_0 \frac{2k_x k_y}{|\mathbf{k}|^2} \\ &= \Delta_0 \sin^2 \theta \sin 2\phi.\end{aligned}\quad (5)$$

These two states are degenerate since we assume a spherical Fermi surface. As shown in Fig.1 the gap function for the $x^2 - y^2$ state is zero on the lines $k_x = k_y$ and $k_x = -k_y$ on the Fermi surface and these lines intersect at points $(0, 0, \pm k_F)$. The density of states is obtained as

$$\frac{N_{x^2-y^2}(E)}{N_0} = \begin{cases} \frac{x}{\pi} \left[\int_0^1 \frac{K(u)}{\sqrt{1-xu}} du + \int_0^{1-x} \frac{K(u+x)}{\sqrt{u(u+x)}} du \right] & \text{if } x < 1 \\ \frac{x}{\pi} \int_0^{\frac{1}{x}} \frac{K(u)}{\sqrt{1-xu}} du & \text{if } x \geq 1 \end{cases} \quad (6)$$

where $x = E/\Delta_0$ and $K(k)$ is the complete elliptic integral of the first kind given by

$$K(k) = \int_0^{\frac{\pi}{2}} \frac{1}{\sqrt{1 - k^2 \sin^2 \theta}} d\theta. \quad (7)$$

For $E \ll \Delta_0$, we obtain

$$\frac{N_{x^2-y^2}(E)}{N_0} \approx \frac{E}{2\Delta_0} \log \frac{\alpha\Delta_0}{E}, \quad (8)$$

where α is obtained numerically as $\alpha = 16.0$. We plot $N(E)$ for the polar and $x^2 - y^2$ states as a function of E in Fig. 2. The densities of states for various states were calculated numerically by Hasselbach *et al.*, [17] but they did not notice the logarithmic dependence.

The $E \log(\alpha\Delta_0/E)$ dependence of the density of states is a general property of anisotropic superconductors with intersecting line nodes in the gap function on the Fermi surface. Near the points of intersection of line nodes, we can write the gap function as

$$\Delta_{\mathbf{k}} \sim \Delta_0 \xi \eta, \quad (9)$$

by choosing suitable variables ξ and η on the Fermi surface. For $x = E/\Delta_0 \ll 1$, the density of states due to these line nodes is obtained as

$$\begin{aligned}N(E) &\sim N_0 \int_{-1}^1 d\xi \int_{-1}^1 d\eta \text{Im} \frac{E}{\sqrt{(\Delta_0 \xi \eta)^2 - E^2}} \\ &= 4N_0 x \left[\int_0^x d\xi \int_0^1 d\eta \frac{1}{\sqrt{x^2 - (\xi \eta)^2}} \right]\end{aligned}$$

$$\begin{aligned}
& + \int_x^1 d\xi \int_0^{\frac{x}{\xi}} d\eta \frac{1}{\sqrt{x^2 - (\xi\eta)^2}} \Big] \\
& = 2\pi N_0 \frac{E}{\Delta_0} \log \frac{2\Delta_0}{E},
\end{aligned} \tag{10}$$

as obtained in eq.(8) for the $x^2 - y^2$ state.

In order to show that $N(E) \propto E \log(\alpha\Delta_0/E)$ can be observed experimentally, we calculate the NMR relaxation rate T_1^{-1} , which is given by

$$\begin{aligned}
\frac{(T_1)_{\text{normal}}}{(T_1)_{\text{super}}} & = 2 \int_0^\infty \left(-\frac{\partial f(E)}{\partial E} \right) \\
& \times \left\{ \left(\frac{N(E)}{N_0} \right)^2 + \left(\frac{M(E)}{N_0} \right)^2 \right\} dE,
\end{aligned} \tag{11}$$

where

$$M(E) = N_0 \int \frac{d\Omega}{4\pi} \text{Im} \frac{\Delta_{\mathbf{k}}}{\sqrt{\Delta_{\mathbf{k}}^2 - E^2}}. \tag{12}$$

For polar and $x^2 - y^2$ states, for which the s -wave component is not included in the gap function, we obtain $M(E) = 0$. We calculate eq.(11) numerically by assuming the temperature dependence of the maximum gap to be

$$\Delta_0(T) = 1.76 k_B T_c \tanh \left(1.74 \sqrt{\frac{T_c}{T} - 1} \right), \tag{13}$$

which is the approximate temperature dependence of the energy gap in s -wave superconductors in the weak coupling limit. Since we are interested in the effect of the logarithmic correction in the density of states due to the intersection of the line nodes in the gap function, we use eq.(13) for the polar and $x^2 - y^2$ states.

In Fig. 3 we plot T_1^{-1} normalized by the value for the normal state as a function of temperature. In order to see the temperature dependence clearly we plot $1/(T_1 T^3)$ as a function of temperature in Fig. 4, which shows that while a T^3 dependence of T_1^{-1} is obtained for $T \leq T_c/2$ for the polar state, $1/(T_1 T^3)$ diverges as the temperature decreases for the $x^2 - y^2$ state. At low temperatures we obtain $T_1^{-1} \propto T^3 (\log T)^2$ for the $x^2 - y^2$ state.

The experimental results for the heavy fermion superconductors UBe₁₃, [1] CeCu₂Si₂, [2] URu₂Si₂ [3, 4, 5] and UPd₂Al₃ [6, 7] are well fitted by $T_1^{-1} \propto T^3$ and no logarithmic correction is observed. It can be concluded that the line nodes in the gap function do not intersect on the Fermi surface. This provides a restriction for the symmetry of the gap function and the Fermi surface. If the gap function has the symmetry with $k_x^2 - k_y^2$ or $k_x k_y$, the Fermi surface should open in the $(0, 0, \pm 1)$ direction, as in the quasi-one or quasi-two dimensional case.

The temperature dependence of the specific heat for various anisotropic superconductors has been calculated by Hasselbach *et al.* [17] They obtained the deviation from linear dependence in the density of states and $C(T)/T$ for the states with intersecting line nodes numerically, although they did not observe the logarithmic corrections. From the temperature dependence of the specific heat, it can be concluded that intersection of the line nodes does not occur on the Fermi surface.

In conclusion, we have shown that intersection of the line nodes results in an $E \log(\alpha\Delta_0/E)$ dependence in the density of states. In that case deviation from power law behavior can be observed in the temperature dependence of the relaxation rate T_1^{-1} and the specific heat. In experiments on heavy fermion superconductors, no deviation from power law dependence has been observed. This implies a the strong restriction on the symmetry of the gap function, i.e. the gap function should not have saddle points on the Fermi surface.

The author would like to thank Professor Y. Kohori for discussion on the experimental results and Professor T. Kohara for valuable comments.

References

- [1] D.E. MacLaughlin, C. Tien, W.G. Clark, M.D. Lan, Z. Fisk, J.L. Smith and H.R. Ott: Phys. Rev. Lett. **53** (1984), 1833.
- [2] Y. Kitaoka, K. Ueda, T. Kohara, K. Asayama, Y. Onuki and T. Komatsubara: J. Magn. Magn. Mat. **52** (1985) 341.
- [3] T. Kohara, Y. Kohori, K. Asayama, Y. Kitaoka, M.B. Maple and M.S. Torikachvili: *Theoretical Experimental Aspects of Valence Fluctuation and Heavy Fermions* (Plenum 1987) p.337.
- [4] K. Matsuda, Y. Kohori and T. Kohara: J. Phys. Soc. Jpn. **65** (1996) 679.
- [5] Y. Kohori, K. Matsuda and T. Kohara: J. Phys. Soc. Jpn. **65** (1996) 1083.
- [6] M. Kyogaku, Y. Kitaoka, K. Asayama, C. Gebol and C. Schank: J. Phys. Soc. Jpn. **62** (1993) 4016.
- [7] Y. Kohori, K. Matsuda and T. Kohara: Solid State Commun. **95** (1995) 121.
- [8] G.E. Volovik and L.P. Gor'kov: Sov. Phys. JETP **61** (1985) 843.
- [9] For review see M. Sigrist and K. Ueda: Rev. Mod. Phys. **63** (1991) 239.
- [10] K. Ueda and T.M. Rice: *Theory of Heavy Fermions and Valence Fluctuations*, eds. Kasuya and T. Sato, (Springer 1985) p.267.

- [11] S. Schmit-Rink, K. Miyake and C.M. Varma: Phys. Rev. Lett. **57** (1986) 2575.
- [12] P. Hirshfeld, D. Vollhard and P. Wölfle: Solid State Commun. **59** (1986) 111.
- [13] T. Imai, T. Shimizu, H. Yasuoka, Y. Ueda and K. Kosuge: J. Phys. Soc. Jpn. **57** (1988) 2280.
- [14] K. Kitaoka, S. Hiramatsu, Y. Kohori, K. Ishida, T. Kondo, H. Shibai, K. Asayama, H. Takagi, S. Uchida, H. Iwabuchi and S. Tanaka: Physica C 153-155 (1988) 83.
- [15] M. Takigawa, H. Yasuoka and G. Saito: J. Phys. Soc. Jpn. **56** (1987) 873.
- [16] H. Mayaffre, P. Wzietek, D. Jérôme, C. Lenoir and P. Batai: Phys. Rev. Lett. **75** (1995) 4122.
- [17] K. Hasselbach, J.R. Kirtley and J. Floquet: Phys. Rev. B **47** (1993) 509.

Figure 1: The gap function for the $x^2 - y^2$ state

Figure 2: The densities of states for the $x^2 - y^2$ state (solid line) and the polar state (broken line).

Figure 3: The NMR relaxation rates $(T_1)_{\text{normal}}/(T_1)_{\text{super}}$ for the $x^2 - y^2$ state (solid line) and the polar state (broken line) as a function of temperature.

Figure 4: The NMR relaxation rates, $(T_1 T^3)_{T=T_c}/(T_1 T^3)_{\text{super}}$, for the $x^2 - y^2$ state (solid line) and the polar state (broken line) as a function of temperature.

This figure "fig1.gif" is available in "gif" format from:

<http://arXiv.org/ps/supr-con/9609003v1>





